

Characteristics

This white polyisoprene synthetic material has all of the preferred physical characteristics of natural rubber latex without the natural rubber proteins and allergens. The interior provides improved donning even when hands are damp during double gloving, due to the aqueous gel.

Features:

- Unique Hydrogel Interior for Damp-hand Donnability
- Bisque Finish for an Improved Wet/Dry Grip
- Non-Latex for No Risk of Latex Allergens



**Surgical Glove
Sterile**

*Prestige® PI Select
Polyisoprene*

Series 146



PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
5.5	146550	50 pairs/box, 4 boxes/case	Gloves, Surgical, Polyisoprene, Sterile, Powder-Free, White
6	146600	50 pairs/box, 4 boxes/case	
6.5	146650	50 pairs/box, 4 boxes/case	
7	146700	50 pairs/box, 4 boxes/case	
7.5	146750	50 pairs/box, 4 boxes/case	
8	146800	50 pairs/box, 4 boxes/case	
8.5	146850	50 pairs/box, 4 boxes/case	
9	146900	50 pairs/box, 4 boxes/case	

View this product on
our website:



Product Solutions You Trust




Prestige® PI Select

POWDER-FREE

POLYISOPRENE

SURGICAL GLOVES



Prestige® PI Select is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D3577	Standard Specification for Rubber Surgical Gloves
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens

Average Length	Average Palm Thickness	Average Finger Thickness
11.6 in ♦ 295 mm	8.0 mil ♦ 0.20 mm	9.8 mil ♦ 0.25 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	25	24
ASTM Requirement Min. (Mpa)	17	12
Elongation (%)	850	820
ASTM Requirement Min. (%)	650	490



Intertek
Innovative Healthcare Corporation
is certified to ISO 13485:2016 QMS
for medical devices.



**INNOVATIVE
HEALTHCARE
CORPORATION**

Product Solutions You Trust

1-800-272-1533