


Characteristics

Pulse® LOGIC™ 200 is the culmination of decades of medical glove evolution. This nitrile medical glove is thinner than other gloves, but it is stronger and far more elastic than normal nitrile gloves. The softer, more relaxed formulation is ideal for dental professionals with its ability to reduce muscle fatigue. Incredible elasticity and comfort, all very logical. All very Pulse® LOGIC™.

Features:

- ThinFilm for Increased Tactile Sensitivity
- Low Modulus for a Softer, More Comfortable Fit
- Textured Finish for an Improved Wet/Dry Grip
- Non-Latex for No Risk of Latex Allergens



Pulse® LOGIC™ 200

**Nitrile
Series 172**

**Non-Sterile
Exam Glove**



PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
XS	172050	200 Gloves/box, 10 boxes/case	Gloves, Exam, Nitrile, Non-Sterile, Chemo, Powder-Free, Textured, Thinfilm
S	172100	200 Gloves/box, 10 boxes/case	
M	172200	200 Gloves/box, 10 boxes/case	
L	172300	200 Gloves/box, 10 boxes/case	
XL	172350	200 Gloves/box, 10 boxes/case	


View this product on
our website:



Product Solutions You Trust



Pulse[®] LOGIC[™] 200 Nitrile Exam Gloves



✓ Tested for use with
Chemotherapy Drugs

- ✓ Non-Latex for No Risk of Latex Allergens
- ✓ Incredible Elasticity and Comfort
- ✓ Stronger and Thinner than Other Nitrile Exam Gloves

Pulse[®] LOGIC[™] 200 Nitrile is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D6319	Standard Specification for Nitrile Examination Gloves for Medical Application
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens

Average Length	Average Palm Thickness	Average Finger Thickness
9.5 in ♦ 240 mm	2.0 mil ♦ 0.05 mm	2.3 mil ♦ 0.06 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	30	35
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	720	700
ASTM Requirement Min. (%)	500	400



Intertek

Innovative Healthcare Corporation is certified to ISO 13485:2016 QMS for medical devices.

Chemotherapy Drug Permeation (Breakthrough detection time in minutes, 0.01µg/cm ² /min.)	(ASTM D6978) Breakthrough Detection Time
Cisplatin (1.0 mg/mL)	>240
Cyclophosphamide (Cytosan) (20.0 mg/mL)	>240
Dacarbazine (10.0 mg/mL)	>240
Doxorubicin Hydrochloride (2.0 mg/mL)	>240
Etoposide (20.0 mg/mL)	>240
Fluorouracil (50.0 mg/mL)	>240
Ifosfamide (50.0 mg/mL)	>240
Methotrexate (25.0 mg/mL)	>240
Mitomycin C (0.5 mg/mL)	>240
Mitoxantrone (2.0 mg/mL)	>240
Paclitaxel (6.0 mg/mL)	>240
Vincristine Sulfate (1.0 mg/mL)	>240
*Carmustine (BiCNU) (3.3 mg/mL)	DO NOT USE
*Thiotepa (10.0 mg/mL)	DO NOT USE

*Please call Customer Service at 1 800 272 1533 for a list of products appropriate for use with this drug.