

# Pulse® PRECISE™

## Nitrile Exam Gloves Series 176

Pulse® PRECISE™ is a thinner, lighter nitrile glove that provides increased tactile sensitivity for the user while maintaining its exceptional durability. Textured fingertips create excellent gripping properties. Automated flat stacking allows each glove to be dispensed easily and without waste.

Characteristics: Non-Sterile, Powder-Free



SIZE	ITEM NO.
XS	176050
S	176100
M	176200
L	176300
XL	176350
XXL	176400

XS-XL : 250 Gloves/Box, 10 Boxes/Case  
XL : 230 Gloves/Box, 10 Boxes/Case

### Features:

- Flat Stacking = Gloves Dispense Easily, One by One
- 250 Gloves Per Box = Lower Cost Per Glove
- Finger Textured = An Improved Wet/Dry Grip



Manufactured in compliance with multiple international standards, including ASTM D6319, ASTM D5151, and ASTM F1671

Tested for use with Chemotherapy Drugs as per ASTM D6978 Standard Practice for Assessment of Medical Gloves to Permeation by Chemotherapy Drugs Minimum Breakthrough Detection Time in Minutes:			
Azacytidine (25.0 mg/ml)	>240	Ifosfamide (50.0 mg/ml)	>240
Carboplatin (10.0 mg/ml)	>240	Irinotecan (20.0 mg/ml)	>240
Carmustine (3.3 mg/ml)	23.3	Methotrexate (25.0 mg/ml)	>240
Cisplatin (1.0 mg/ml)	>240	Mitomycin C (0.5 mg/ml)	>240
Cyclophosphamide (20.0 mg/ml)	>240	Mitoxantrone (2.0 mg/ml)	>240
Dacarbazine (10.0 mg/ml)	>240	Oncovin (1.0 mg/ml)	>240
Docetaxel (10.0 mg/ml)	>240	Oxaliplatin (5.0 mg/ml)	>240
Doxorubicin Hydrochloride (2.0 mg/ml)	>240	Paclitaxel (6.0 mg/ml)	>240
Epirubicin (2.0 mg/ml)	>240	Thiotepa (10.0 mg/ml)	58.2
Etoposide (20.0 mg/ml)	>240	Vincristine Sulfate (1.0 mg/ml)	>240
Fluorouracil (50.0 mg/ml)	>240	Vinorelbine (10.0 mg/ml)	>240
Gemcitabine (38.0 mg/ml)	>240	Also Tested: Fentanyl Citrate (100 mcg/2ml)	>240

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	37.5	33.9
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	655	577
ASTM Requirement Min. (%)	500	400

Average Length	9.5 in ♦ 240 mm
Average Palm Thickness	2.5 mil ♦ 0.06 mm
Average Finger Thickness	3.3 mil ♦ 0.08 mm

Please note that Carmustine and Thiotepa have extremely low permeation times of 23.3 minutes and 58.2 minutes respectively  
Caution: In compliance with ASTM D6978, the testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on single layer glove material. It is the users' responsibility to determine the applicability of these gloves for their intended use with chemotherapy drugs.



Product Solutions You Trust

View this product on our website:

