

NITRIDERM® EP ORANGE®

Nitrile Exam Gloves Extra Protection Series 189

Orange - The universal symbol for caution. Ideal for EMS, police and fire, hazmat functions, spills, etc. This powder-free nitrile synthetic glove has an extended cuff length to provide extra protection in high-risk situations. Excellent donning properties in a soft, low modulus formula. Textured, slightly tacky surface for a better grip.

Characteristics: Powder-Free, Non-Sterile, Orange color

SIZE	ITEM NO.
S	189100
M	189200
L	189300
XL	189350
XXL	189400
XXXL	189450

S-XL: 100 Gloves/Box, 10 Boxes/Case
XXL-XXXL: 80 Gloves/Box, 10 Boxes/Case

Tested for use with
Chemotherapy Drugs
AND **Fentanyl Citrate**



Features:

- 6.5 mil Finger Thickness = Extra Protection
- Textured Finish = an Improved Wet/Dry Grip
- Non-Latex = No Risk of Latex Allergens

Manufactured in compliance with multiple international standards, including ASTM D6319, ASTM D5151, ASTM F1671, and ASTM D6978

Tested for use with Chemotherapy Drugs as per ASTM D6978			
Standard Practice for Assessment of Medical Gloves to Permeation by Chemotherapy Drugs			
Minimum Breakthrough Detection Time in Minutes:			
Azacytidine (25.0 mg/ml)	>240	Ifosfamide (50.0 mg/ml)	>240
Carboplatin (10.0 mg/ml)	>240	Irinotecan (20.0 mg/ml)	>240
Carmustine (3.3 mg/ml)	12.9	Methotrexate (25.0 mg/ml)	>240
Cisplatin (1.0 mg/ml)	>240	Mitomycin C (0.5 mg/ml)	>240
Cyclophosphamide (20.0 mg/ml)	>240	Mitoxantrone (2.0 mg/ml)	>240
Dacarbazine (10.0 mg/ml)	>240	Oncovin (1.0 mg/ml)	>240
Docetaxel (10.0 mg/ml)	>240	Oxaliplatin (5.0 mg/ml)	>240
Doxorubicin Hydrochloride (2.0 mg/ml)	>240	Paclitaxel (6.0 mg/ml)	>240
Epirubicin (2.0 mg/ml)	>240	Thiotepa (10.0 mg/ml)	45.0
Etoposide (20.0 mg/ml)	>240	Vincristine Sulfate (1.0 mg/ml)	>240
Fluorouracil (50.0 mg/ml)	>240	Vinorelbine (10.0 mg/ml)	>240
Gemcitabine (38.0 mg/ml)	>240	Also Tested: Fentanyl Citrate (100 mcg/2ml)	>240

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	32	27
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	650	560
ASTM Requirement Min. (%)	500	400

Average Length	11.5 in ♦ 290 mm
Average Palm Thickness	5.5 mil ♦ 0.14 mm
Average Finger Thickness	6.5 mil ♦ 0.17 mm

Please note that Carmustine and Thiotepa have extremely low permeation times of 12.9 minutes and 45.0 minutes respectively.

Warning: Do not use with Carmustine. Warning: Do not use with Thiotepa.

Caution: In compliance with ASTM D6978, the testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on single layer glove material. It is the users' responsibility to determine the applicability of these gloves for their intended use with chemotherapy drugs.



Intertek

Innovative Healthcare Corporation is certified to ISO 13485:2016 QMS for medical devices.



**INNOVATIVE
HEALTHCARE
CORPORATION**

www.ihcsolutions.com
1-800-272-1533

View this product
on our website:



Product Solutions You Trust