

## Product Literature

#### **Characteristics**

Made from non-latex, polychloroprene synthetic polymer, these new Blackwork® Chloroprene exam gloves offer all of the benefits of natural rubber latex, with none of the allergen problems associated with latex. These exam gloves are the most comfortable gloves you'll ever wear! They're incredibly soft, unbelievably elastic, and yet they're still amazingly strong. Textured finish provides excellent wet or dry gripping ability. Black color.



**Blackwork** • Chloroprene Black Gloves

Exam Glove Non-Sterile



### Features:

- Textured Finish for an Improved Wet/Dry Grip
- Non-Latex for No Risk of Latex Allergens
- Low Modulus for a Softer, More Comfortable Fit

#### PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION	
XS	1010	100 Gloves/box, 10 boxes/case		
S	1020	100 Gloves/box, 10 boxes/case		
М	1030	100 Gloves/box, 10 boxes/case	Gloves, Exam, Chloroprene, Non-Sterile, Powder-Free, Textured, Black	
L	1040	100 Gloves/box, 10 boxes/case	Thorr-oteriie, i owder-i ree, rextured, black	
XL	1050	100 Gloves/box, 10 boxes/case		



# Specification Sheet



Blackwork Chloroprene is manufactured in compliance with multiple international standards, including the following:

Designation	Standard	
ASTM D6977	Standard Specification for Polychloroprene Examination Gloves for Medical Application	
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves	
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens	

Average Length	Average Palm Thickness	Average Finger Thickness	
9.5 in <b>→</b> 240 mm	2.8 mil ◆ 0.07 mm	3.5 mil ◆ 0.09 mm	

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	15.9	20.9
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	817	732
ASTM Requirement Min. (%)	500	400



